

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C08F 210/06, 210/14, C08K 5/00 //</b> <b>(C08K 5/00, 5:13, 5:524)</b>		<b>A1</b>	(11) International Publication Number: <b>WO 96/24623</b> (43) International Publication Date: <b>15 August 1996 (15.08.96)</b>
(21) International Application Number: <b>PCT/GB96/00201</b> (22) International Filing Date: <b>30 January 1996 (30.01.96)</b> (30) Priority Data: <b>95/1057</b> <b>9 February 1995 (09.02.95)</b> <b>ZA</b> (71) Applicant (for all designated States except US): <b>SASTECH (PROPRIETARY) LIMITED [ZA/ZA]; 1 Sturdee Avenue, Rosebank 2196 (ZA).</b> (71) Applicant (for SD only): <b>SASOL CHEMICALS EUROPE LIMITED [GB/GB]; 1 Hockley Court, 2401 Stratford Road, Hockley Heath, Solihull, West Midlands B94 6NW (GB).</b> (72) Inventors; and (75) Inventors/Applicants (for US only): <b>JOUBERT, Dawid, Johannes [ZA/ZA]; 60 Leeukop Street, Vaalpark, Sasolburg 9570 (ZA). POTGIETER, Antonie, Hermanus [ZA/ZA]; 17 Wagner Street, Secunda 2302 (ZA). POTGIETER, Ignatius, Hendrik [ZA/ZA]; 15 Ramsbottom Street, SE2 Vanderbijlpark 1911 (ZA). TINCUL, Ioan [RO/ZA]; 27 Oerder Crescent, Sasolburg 9570 (ZA).</b> (74) Agent: <b>ABLEWHITE, Alan, James; Marks &amp; Clerk, 57-60 Lincoln's Inn Fields, London WC2A 3LS (GB).</b>			(81) Designated States: <b>AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</b>  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: <b>PROPYLENE PENTENE-1 COPOLYMERS, METHOD OF PREPARATION THEREOF AND COMPOSITION CONTAINING THEM</b>			
(57) Abstract <p>The invention provides a copolymer of propylene and pentene, together with a process for producing such copolymer and a polymer composition. In the process, propylene and pentene are reacted in a reaction zone at a pressure of 60kg/cm<sup>2</sup> and temperature of 0-100 °C for 20-480 minutes in the presence of a Ziegler-Natta catalyst or catalyst system. The polymer composition has several components, namely the above copolymer, a phenolic stabilizer, an organic phosphite stabilizer, a thioether stabilizer and at least one metal salt of a higher aliphatic acid, with the proviso that at least one of the organic phosphite stabilizer, the thioether stabilizer and said salt must be present, so that up to two thereof can optionally be omitted.</p>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

PROPYLENE PENTENE - 1 COPOLYMERS, METHOD OF PREPARATION THEREOF  
AND COMPOSITION CONTAINING THEM

THIS INVENTION relates to copolymerization. It relates in particular to a copolymer of propylene and 1-pentene, to a process for producing such a copolymer, and to a polymer composition which includes such a copolymer.

5 According to a first aspect of the invention, there is provided, broadly, a copolymer of propylene and 1-pentene.

The copolymer may, more particularly, have a random arrangement of propylene and 1-pentene, ie it may be a random copolymer of propylene and 1-pentene. The copolymer  
10 may be thermoplastic, and may have crystalline and amorphous sequences.

The copolymer may further be characterized by the substantial absence of monomer sequences other than propylene and 1-pentene.

15 About 0,05% to 20% by mass of the copolymer may be derived from 1-pentene, with the balance thus being derived from propylene.

The melt flow index of the copolymer may be in the range of about 0,01 to about 200g/10 minutes, preferably in the  
20 range 0,5 to about 60g/10 minutes.

The copolymer may comply with the formula

$$IS > 0,5 Y + 5$$

where IS is the impact strength thereof, expressed in Kj/m<sup>2</sup>, and Y is the weight percent of 1-pentene in the copolymer.

25 The copolymer may also have a haze value lower than 7,5%

when measured according to ASTM 1003-92, on a film of 100 $\mu$ m.

5 The copolymer may be that obtained by reacting propylene and 1-pentene in a reaction zone, while maintaining a pressure between 1 and 60 kg/cm<sup>2</sup> in the zone, at a reaction temperature between 0°C and 100°C, and for a reaction time between 20 minutes and 8 hours, in the presence of a suitable Ziegler-Natta catalyst or catalyst system. Still more particularly, the copolymer may be that obtained by  
10 continuously varying, during the reaction of the propylene and the 1-pentene, the ratio of the concentration of the propylene to that of the 1-pentene.

Thus, according to a second aspect of the invention, there is provided a process for producing a copolymer, which  
15 process comprises reacting propylene and 1-pentene in a reaction zone, while maintaining a pressure between 1 and 60 kg/cm<sup>2</sup> in the zone, at a reaction temperature between 0°C and 100°C, and for a reaction time between 20 minutes and 8 hours, in the presence of a suitable Ziegler-Natta  
20 catalyst or catalyst system.

The process may include continuously varying the ratio of the concentration of the propylene to that of the 1-pentene in the reaction zone, so that the copolymer has a random arrangement of propylene and 1-pentene. In other words,  
25 the copolymer is then a random copolymer of propylene and 1-pentene, which can also be referred to as 'n-pentene-1'.

While the reaction temperature can be in the range of 0°C to 100°C as stated hereinbefore, it is preferably in the range of 20°C - 80°C, still more preferably in the range  
30 40°C - 70°C.

Since propylene is a gas at atmospheric pressure, the reaction zone is thus provided by a closed reaction vessel,

with the zone pressure being in said range of 1 - 60 kg/cm<sup>2</sup>. Preferably, the pressure is in the range 3 - 30 kg/cm<sup>2</sup>, more preferably in the range 6 - 14 kg/cm<sup>2</sup>.

5 The reaction will thus be continued for a sufficient period of time to obtain a desired degree of conversion of the monomers. Typically, the conversion can be in the range 10% - 95%. Thus, the reaction time will normally be between said 20 minutes and 8 hours, preferably between 40 minutes and 2 hours.

10 The reaction is preferably carried out in a single reaction zone, ie a single stage reactor vessel is preferably used. The reaction can be effected in a batch fashion, with all the monomers, ie the propylene and 1-pentene, being added simultaneously at the start of the reaction to the reaction  
15 zone, and no product being removed therefrom during the course of the reaction. Thus, the continuous variation in the ratio of the concentration of the propylene to that of the 1-pentene during the reaction is achieved by virtue of the monomers being consumed at unequal rates during the  
20 reaction, ie the monomers have different reaction rates. Instead, the process may be a semi-continuous process, wherein at least one of the monomers is added continuously to the reaction zone over a period of time with the other monomer then either also being added continuously over the  
25 period of time or being added at the start of the reaction, and with no products being removed. The continuous variation in the relative concentrations of the monomers is then achieved through the unequal rates of consumption of the monomers during the reaction, as well as rates of  
30 addition of the monomers. In yet a further embodiment, the process may be a continuous process, involving the continuous addition of the monomers to the reaction zone, and the continuous removal of products therefrom. In such case, the continuous variation in the relative  
35 concentrations of the monomers is effected by means of the

unequal rates of consumption thereof, as well as by the addition rates of the monomers and the withdrawal rate of product from the reaction zone.

5 The reaction is preferably also carried out in slurry phase. Accordingly, the monomers and/or the catalyst may be suspended in a suitable inert slurrying agent. The slurrying agent may be a saturated, aliphatic or cyclo-aliphatic liquid hydrocarbon. In particular the hydrocarbon may have from 2 - 12 carbon atoms. Most  
10 preferred are aliphatic hydrocarbons having 6 and 7 carbon atoms. The volume or proportion of slurrying agent used is not critical, but should be sufficient to permit good agitation of the resultant slurry, and efficient heat transfer. Thus, sufficient slurrying agent may be used to  
15 achieve a slurry concentration in the range of 4g - 400g of polymer per liter of slurrying agent, preferably 50 - 250g/l.

The molecular weight of the resultant random copolymer can be regulated by adding hydrogen to the reaction zone. The  
20 greater the amount of hydrogen added, the lower will be the molecular weight of the random copolymer. A hydrogen partial pressure of 0,1 - 2 kg/cm<sup>2</sup> is suitable for a reaction zone pressure of 3 - 30 kg/cm<sup>2</sup>.

Any Ziegler-Natta catalyst or catalyst system, suitable for  
25 propylene polymerization, can, at least in principle, be used. Thus, a catalyst system comprising a titanium-based Ziegler-Natta catalyst and, as a co-catalyst, an organo-aluminium compound, and wherein the atomic ratio of aluminium to titanium in the catalyst system is between  
30 0,1:1 and 100:1, preferably 0,65:1 and 65:1, may be used.

Sufficient of the titanium-based Ziegler-Natta catalyst should then be used such that the concentration of titanium is at least 0,0001 mole %, based on the total monomer

addition to the reaction zone. Preferably, the concentration thereof should be in the range 0,0003 - 0,15 mole % titanium.

5 Typical titanium components of the Ziegler-Natta catalyst are titanium trichlorides of  $\alpha$ ,  $\beta$ ,  $\gamma$  and  $\delta$  type, and titanium trichlorides or titanium tetrachloride carried on a support. Catalyst support and activation can be effected in known fashion. For the preparation of a titanium catalyst, halides or alcoholates of trivalent or  
10 tetravalent titanium are normally used.  $\text{TiCl}_4$  is especially preferred.

In addition to the trivalent and tetravalent titanium compounds and the support or carrier, the catalyst can also contain electron-donor compounds, eg mono or poly  
15 functional carboxyl acids, carboxyl anhydrides and esters, ketones, ethers, alcohols, lactones, or phosphorous or silicon organic compounds. Electron-donor compounds improve activity, stereoregularity and granulometric properties of the catalyst.

20 A preferred titanium-based catalyst is  $(\text{TiCl}_3)_2$ ,  $\text{AlCl}_3$ , commercially available with a content of 76,5-78,5  $\text{TiCl}_4$  weight percent. Another preferred titanium catalyst is  $\delta\text{-TiCl}_3$ ,  $(\text{AlCl}_3)^{1/2}$ , (n-propyl benzoate), which is commercially available.

25 Typical organo aluminium compounds which can be used in combination with the titanium-based catalyst are compounds expressed by the formula  $\text{Al R}_m \text{X}_{3-m}$  wherein R is hydrogen or a hydrocarbon residue of 1-15 carbon atoms, X is a halogen atom or an alkoxy group of 1-15 carbon atoms, and m is a  
30 number represented by  $0 < m < 3$ . Specific examples of suitable organo aluminium compounds which can be used are: a trialkyl aluminium, a trialkenyl aluminium, a partially alkoxyated alkyl aluminium, an alkyl aluminium

sesquialc oxide, a partially halogenated alkyl aluminium, an alkyl aluminium sesquihalide, an alkyl aluminium dihalide, a partially hydrogenated alkyl alumina, an alkyl aluminium dihydride, and an alkyl aluminium oxyhalide. The most preferred organo aluminium compound is diethylaluminium chloride. Triethyl aluminium is the most preferred compound when working with magnesium chloride supported titanium catalyst in the presence of an electron donor.

The copolymer obtained from the process shows a random monomer distribution controlled by the ratio of the monomers used, and the reaction conditions. Thus, in the copolymer, the portion attributed to propylene can be in the range of 80 - 99,95% by weight, based on the weight of the copolymer, preferably in the range of 94% - 99%. In other words, the portion attributed to 1-pentene can be in the range of 0,05% - 20% by weight, preferably in the range of 1 - 6% by weight, as stated hereinbefore.

The Applicant is aware that polypropylene copolymers are sensitive to oxidation and normally are not used without adequate stabilization. The copolymers according to this invention can thus be stabilized in the same fashion as for the propylene copolymer stabilization.

An improved stabilization system for stabilization of copolymers according to the invention, thereby decreasing their termooxidative degradation and improving their long term heat stability is, however, also provided.

Thus, according to a third aspect of the invention, there is provided a polymer composition, which comprises  
as component (i), a copolymer of propylene and 1-pentene;  
as component (ii), at least one phenolic stabilizer;  
and

as component (iii), at least one organic phosphite stabilizer; and/or

as component (iv), at least one thioether stabilizer; and/or

- 5 as component (v), at least one metal salt of a higher aliphatic acid, with the proviso that at least one of components (iii), (iv) and (v) is present.

The copolymer of propylene and 1-pentene may thus be as hereinbefore described.

- 10 Component (ii) may comprise an organic phenolic stabilizer having a molecular mass exceeding 300 and/or a monomeric phenolic stabilizer.

A large range of known phenolic compounds can be used as the organic phenolic stabilizer or antioxidant. These include alkylphenols, hydroxyphenylpropionates, hydroxybenzyl compounds, and alkylidene bisphenols. As mentioned, the preferred phenolic stabilizers are those with molecular mass greater than 300. The most preferred phenolic stabilizers are those with a molecular mass greater than 600. Examples of preferred stabilizers are

- 20 - tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydro-cinnamate) methane  
- octadecyl-3-(3,5-di-t-butyl-4-hydroxyphenyl) propionate  
25 - 1,3,5-tris (3',5'-di-t-butyl-4'-hydroxybenzyl)-s-triazine-2,4,6-(1H,3H,5H) trione  
- 2,2'-thiodiethyl-bis-(3,5-di-t-butyl-4-hydroxyphenyl)-propionate

30 A monomeric phenolic stabilizer is a dual functional compound having an antioxidant function and also being capable of polymerization, ie having a polymerizable group. It can be incorporated in the copolymer by a physical method, eg by melt mixing it with the copolymer or by

mixing the copolymer with the homopolymer of the monomeric phenolic stabilizer or antioxidant. It can, however, also be incorporated in the copolymer by copolymerization. The preferred method of incorporation of the monomeric phenolic stabilizer is by graft copolymerization with the copolymer, initiated by radical initiators and/or by mechanical shearing in a molten state. The preferred radical initiators are peroxides. Examples of classes of peroxides which can be used are diacyl peroxides, dialkyl peroxidicarbonates, peresters, alkyl hydroperoxides, and dialkyl peroxides. The most preferred peroxide is the dicumyl peroxide.

More particularly, the monomeric phenolic stabilizer has, in addition to the polymerizable group, a hindered phenolic group providing the antioxidant function. Preferred monomeric phenolic stabilizers are those having a 3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl group providing the antioxidant function, attached to a vinyl polymerizable group. Examples of such monomeric phenolic stabilizers are

- 2,6-bis(1,1-dimethylethyl)-4-(1-methylethenyl)phenol
- 2,6-bis(1,1-dimethylethyl)-4-(4-pentenyl)phenol
- 2,6-bis(1,1-dimethylethyl)-4-(3,3-dimethyl-1-butenyl)phenol
- 2,6-bis(1,1-dimethylethyl)-4-(2-propenyl)phenol

The most preferred monomeric phenolic stabilizer is 2,4-bis(1,1-dimethylethyl)-4-(ethenyl)-phenol.

A monomeric phenolic stabilizer grafted onto the copolymer chain inhibits the loss of the antioxidant during processing through volatility, migration or extraction with solvents. The use of a mixture of an organic phenolic stabilizer and a monomeric phenolic stabilizer grafted onto the copolymer is an exceptional combination which brings about particularly beneficial short and long term stabilization effects.

The composition can thus additionally include component (iii). While, at least in principle, any organic phosphite stabilizer can be used, it preferably has a molecular mass in excess of 300. Examples of such organic phosphite stabilizers are:

- tris(2,4-di-t-butylphenyl)phosphite
- tris(4-nonylphenyl)phosphite
- tetrakis(2,4-di-t-butylphenyl)-4,4'-diphenylenebis-phosphonite
- bis(2,4-di-t-butylphenyl)pentaerythritoldiphosphite

The use of an organic phosphite stabilizer together with a phenolic antioxidant and especially with a mixture of an organic phenolic antioxidant and a monomeric phenolic antioxidant grafted onto the copolymer chain increases the stability of the propylene/1-pentene copolymer to thermooxidative degradation, and provides particularly good long term heat stability.

The composition may instead, or additionally, include component (iv). The thioether stabilizer of component (iv) may be selected from the group consisting in dilauryl thiodipropionate, distearyl thiodipropionate, dimyristyl thiodipropionate, and dioctadecyl disulphide.

The presence of such a thioether stabilizer increases the stabilization properties of the phenolic stabilizer or antioxidant. The use of a thioether stabilizer with a mixture of an organic phenolic antioxidant and a monomeric phenolic antioxidant grafted onto the copolymer chain confers excellent degradation stability to the propylene/1-pentene copolymer.

The composition may instead, or additionally, include component (v). The metal salt of component (v) may be an alkaline earth metal salt, such as a magnesium salt, a calcium salt, or a barium salt; an alkali metal salt; a

10

zinc salt; a cadmium salt; or a lead salt of a higher aliphatic acid such as stearic acid, lauric acid, capric acid or palmitic acid. The most preferred metal salt is calcium stearate.

5 When a higher aliphatic acid metal salt is added to a propylene-1-pentene copolymer or a propylene/1-pentene copolymer composition according to this invention, the metal salt is capable of sufficiently absorbing residual chloride originating from the catalyst used to produce the  
10 copolymer.

In one embodiment of the invention, the polymer composition may comprise

- |    |                |   |  |
|----|----------------|---|--|
|    | component (i)  | - | about 100 parts by mass                              |
| 15 | component (ii) | - | 0,01 - 1 part by mass,<br>preferably 0,03 - 0,3 part |
|    | component (v)  | - | 0,01 - 3 parts by mass,<br>preferably 0,05 - 1 part  |

In another embodiment of the invention, the polymer composition may comprise

- |    |                 |   |  |
|----|-----------------|---|--|
| 20 | component (i)   | - | about 100 parts by mass                              |
|    | component (ii)  | - | 0,01 - 1 part by mass,<br>preferably 0,03 - 0,3 part |
|    | component (iii) | - | 0,01 - 1 part by mass,<br>preferably 0,03 - 0,3 part |
| 25 | component (v)   | - | 0,01 - 3 parts by mass,<br>preferably 0,05 - 1 part  |

In yet another embodiment of the invention, the polymer composition may comprise

- |    |                |   |  |
|----|----------------|---|--|
|    | component (i)  | - | about 100 parts by mass                              |
| 30 | component (ii) | - | 0,01 - 1 part by mass,<br>preferably 0,03 - 0,3 part |

11

- component (iv) - 0,01 - 3 parts by mass,  
preferably 0,03 - 0,9 part
- component (v) - 0,01 - 3 parts by mass,  
preferably 0,05 - 1 part

5 In these embodiments, the ratio of the organic phenolic stabilizer to the monomeric phenolic stabilizer can be varied over the entire range possible, ie from 100% of organic phenolic stabilizer and no monomeric phenolic stabilizer to 100% of monomeric phenolic stabilizer and no  
10 organic phenolic stabilizer.

Additionally, the composition may include other antioxidants, light stabilizers, antistatic agents, antiblocking agents, slip agents, nucleating agents, inorganic and organic fillers, inorganic and organic  
15 pigments, blended with the propylene/ 1-pentene copolymers.

The invention will now be described by way of the following non-limiting examples.

#### EXAMPLE 1

1490g of highly purified and dried n-heptane was introduced  
20 into a 5l stainless steel polymerization vessel provided with an agitator driven by an electric motor. After severe purging of the vessel with nitrogen, 2,5g of diethylaluminium chloride ('DEAC') and 0,785g titanium trichloride catalyst (titanium trichloride AA type C  
25 manufactured by Akzo Nobel) were introduced into the vessel, with the n-heptane thus acting as inert slurring agent for the catalysts. The process temperature was set at 60°C, and the mixture stirred for 45 minutes. Thereafter, 20mg of hydrogen was supplied to the  
30 polymerization vessel, together with 20g of 1-pentene.

Simultaneously with the introduction of the 1-pentene, continuous introduction of 600g of propylene at a constant

rate of 15g/minute, was commenced. The pressure increased continuously to 15 bar over the 40 minute period of propylene addition. The slurry was further agitated for another 20 minutes.

5 In a next step, the polymerization vessel was depressurized and the catalyst decomposed in an excess of iso-propanol. The resultant copolymer was then filtered and repeatedly washed with propanol, methanol and acetone. The copolymer was dried in a vacuum oven at 70°C for 24 hours. The yield  
10 of the copolymer was 320g.

The amount of 1-pentene incorporated in the copolymer was 1,24 weight percent. The melt flow index was 1,52; the tensile strength at yield was 32,14 MPa; the Izod notched impact resistance at 23°C was 5,87 KJ/m<sup>2</sup>, and the haze on  
15 pressed film of 100 microns was 1,5.

#### EXAMPLE 2

Copolymerization was carried out under the conditions specified in Example 1 except for the quantity of 1-pentene added, which was 4,8g. The copolymer was obtained at a  
20 yield of 295g. The measured properties of the copolymer are presented in Table 1.

#### EXAMPLE 3

Copolymerization was carried out by the procedure described in Example 1 except for the quantity of 1-pentene added, which was 80g. The yield of the copolymer was 351g. The  
25 measured properties of the copolymer are presented in Table 1.

#### EXAMPLE 4

Copolymerization was performed by the procedure of Example  
30 1 except for the quantity of 1-pentene added, which was 40g. 317g of the copolymer were obtained. The measured properties of the copolymer are presented in Table 1.

EXAMPLE 5

Copolymerization was performed according to the conditions specified in Example 1, except for the quantity of 1-pentene added, which was 132g. The yield of the  
5 copolymer was 650g. The measured properties of the copolymer are presented in Table 1.

EXAMPLE 6

2,5l of highly purified n-heptane was introduced into a 5l stainless steel polymerization vessel provided with an  
10 agitator. After thorough purging of the vessel with nitrogen, 5g of DEAC and 2g of  $TiCl_3$ ,  $(AlCl_3)^{1/3}$ ,  $(n\text{-propylbenzoate})^{1/3}$  catalyst was introduced into the vessel. The process temperature was set to 50°C, and the mixture was stirred for one hour under nitrogen. The  
15 pressure was increased to 1 kg/cm<sup>2</sup> with hydrogen, and 46,4g of 1-pentene were introduced into the polymerization vessel. Simultaneously with the introduction of 1-pentene, the supply of propylene to the polymerization vessel was commenced. The pressure was raised to 6 kg/cm<sup>2</sup> with  
20 propylene addition, and the flow of propylene was adjusted to keep this pressure constant for 120 minutes. Thereafter, the supply of propylene was stopped and the polymerization vessel depressurized. The same procedure of catalyst deactivation, filtration and drying as described  
25 in Example 1 was performed. The yield of the copolymer was 753g. The composition determination and the copolymer characterization was performed as in Example 1. The results are presented in Table 2.

EXAMPLE 7

30 The copolymerization was performed according to the conditions specified in Example 6, except for the quantity of the 1-pentene added, which was 39,7g and the time for polymerization which was 240 minutes. The yield of the copolymer was 1010g. The composition of the copolymer, and  
35 the measured properties are presented in Table 2.

EXAMPLE 8

5 The copolymerization was performed according to the conditions specified in Example 6, except for the quantity of the 1-pentene added, which was 45,5g and the time of the polymerization which was 480 minutes. The yield of the copolymer was 1213g. The composition of the copolymer and the measured properties are presented in Table 2.

EXAMPLE 9

10 The copolymerization was carried out under the conditions specified in Example 6, except for the amount of 1-pentene added, which was 37,5g and the fact that hydrogen was not used in this copolymerization. The yield was 620g. The composition of the copolymer and the measurement of the properties are presented in Table 2.

15 EXAMPLE 10

The copolymerization was carried out under the conditions specified in Example 6, except for the following changes: no hydrogen was used; the amount of 1-pentene added was 96,9g; the reaction temperature was 45°C; the pressure was 7,9 kg/cm<sup>2</sup>; the polymerization time was 60 minutes. The yield was 320g. The composition of the copolymer and the measured properties are presented in Table 2.

20

TABLE 1

	Example 1	Example 2	Example 3	Example 4	Example 5
1. 1-Pentene content	1,24	0,3	6,0	2,8	14
2. Melt flow index	1,52	0,80	1,10	1,61	52,3
3. Tensile strength at yield	32,14	34,3	25,3	30,7	14,96
4. Izod notched impact	5,87	5,56	13,29	6,72	-
5. Haze	1,5	3,7	7,2	2,4	2,6

TABLE 2

	Example 6	Example 7	Example 8	Example 9	Example 10
1. 1-Pentene content	2,2	1,8	1,3	3,0	2,4
2. Melt flow index	26,9	20,4	16,1	0,01	0,01
3. Tensile strength at yield	32,7	33,3	32,9	33,5	34,4
4. Izod notched impact	-	-	-	10,22	8,35
5. Haze	3,0	3,2	4,2	-	-

EXAMPLE 11

33,33g of the propylene/1-pentene copolymer obtained according to Example 1 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,1g of bis(2,4-di-t-butyl)pentaerythritol diphosphite
- 0,1g of calcium stearate
- 0,05g of 2,4-bis(1,1-dimethylethyl)-4-ethenylphenol

The powder mixture was further melt mixed in a Brabender (trade name) at 235°C for 5 minutes together with 0,003g dicumyl peroxide. From this blend a film of 0,2mm was pressed between two aluminium foils using a hydraulic press equipped with a spacer template. The film was pressed at 180°C, for 4 minutes, under 4 tonnes pressure. The film was then placed in a Speccard (trade name) and exposed to oven ageing at 110°C. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was lower than 5%.

EXAMPLE 12

33,33g of the propylene/1-pentene copolymer obtained according to Example 1 was powder mixed with

- 0,1g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,1g of 2,4-bis(1,1-dimethylethyl)-4-ethenylphenol
- 0,1g of calcium stearate

The melt blending and oven exposure were performed as specified in Example 11. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was less than 5%.

EXAMPLE 13

33,33g of the propylene/1-pentene copolymer obtained according to Example 1 was powder mixed with

- 0,1g of bis(2,4-di-t-butylphenyl)pentaerythritoldiphosphite

- 0,1g of 2,4-bis(1,1-dimethylethyl)-4-ethenylphenol
- 0,1g of calcium stearate

The melt blending and oven exposure were performed as specified in Example 11. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was lower than 5%.

#### EXAMPLE 14

33.33g of the propylene/1-pentene copolymer obtained according to Example 1 was powder mixed with

- 0,15g of distearylthiodipropionate
- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,05g of 2,4 bis(1,1-dimethylethyl)-4-ethenylphenol
- 0,1g of calcium stearate

The melt blending and oven exposure were performed as specified in Example 11. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was less than 5%.

#### EXAMPLE 15

33,33g of the propylene/1-pentene copolymer obtained according to Example 1 was used on its own, with no stabilizers added. The melt blending and oven exposure was performed as specified in Example 11. After 12 days local embrittlement was noticeable. The carbonyl which developed due to oxidation increased by 10 times the initial value.

#### EXAMPLE 16

33,33g of the propylene/1-pentene copolymer obtained according to Example 2 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,1g of bis (2,4-di-t-butyl-phenol)pentaerythritol diphosphite
- 0,1g of calcium stearate

- 0,05g of 2,4 bis(1,1-dimethylethyl)-4-ethenylphenol  
The melt blending and oven exposure were performed as  
specified in Example 11. After 365 days of oven ageing no  
sign of brittleness was noticeable. The increase in  
5 carbonyl which developed due to oxidation was less than 5%.

#### EXAMPLE 17

33,33g of the propylene/1-pentene copolymer obtained  
according to Example 3 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-  
10 hydroxyhydrocinnamate)methane  
- 0,1g of bis (2,4-di-t-butyl-phenyl)pentaerythritol  
diphosphite  
- 0,1g of calcium stearate  
- 0,05g of 2,4 bis(1,1-dimethylethyl)-4-ethenylphenol

- 15 The melt blending and oven exposure were performed as  
specified in Example 11. After 220 days of oven ageing  
brittleness was noticed. The carbonyl developed due to  
oxidation increased sharply from 50% on day 210 to 260% on  
day 220.

#### 20 EXAMPLE 18

33,33g of the propylene/1-pentene copolymer obtained  
according to Example 4 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-  
hydroxyhydrocinnamate)methane  
25 - 0,1g of bis (2,4-di-t-butyl-phenyl)pentaerythritol  
diphosphite  
- 0,1g of calcium stearate  
- 0,05g of 2,4 bis(2,4-dimethylethyl)-4-ethenylphenol

- 30 The melt blending and oven exposure were performed as  
specified in Example 11. After 365 days of oven ageing no  
sign of brittleness was noticeable. The increase in  
carbonyl which developed due to oxidation was less than  
40%.

EXAMPLE 19

33,33g of the propylene/1-pentene copolymer obtained according to Example 7 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,1g of bis (2,4-di-t-butyl-phenyl)pentaerythritol diphosphite
- 0,1g of calcium stearate
- 0,05g of 2,4 bis(1,1-dimethylethyl)-4-ethenylphenol

The melt blending and oven exposure were performed as specified in Example 11. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was less than 20%.

EXAMPLE 20

3,33g of the propylene/1-pentene copolymer obtained according to Example 2 was powder mixed with

- 0,05g of tetrakis methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)methane
- 0,1g of bis (2,4-di-t-butyl-phenyl)pentaerythritol diphosphite
- 0,1g of calcium stearate
- 0,05g of 2,4 bis(1,1-dimethylethyl)-4-ethenylphenol

The melt blending and oven exposure were performed as specified in Example 11, with the difference that the Brabender mixing was performed for 10 minutes instead of 5 minutes. After 365 days of oven ageing no sign of brittleness was noticeable. The increase in carbonyl which developed due to oxidation was less than 5%.

EXAMPLE 21

Method of preparation of 2,4-bis(1,1-dimethylethyl)-4-ethenylphenol used in the various examples.

3,5g of boric acid was heated in 150ml of ethylene glycol at 150°C for 30 minutes, in a 500cc flask equipped with a

reflux condenser. 25g of hexamethylenetetramine and 21g of 2,6-bis(1,1-dimethylethyl)phenol were then added and the solution maintained at 148-150°C for 15 minutes. After cooling to 125°C at which stage the first crystals appeared, 150ml of H<sub>2</sub>SO<sub>4</sub> (30%O was added and stirring was continued for another 30 minutes. The resulting slurry was filtered and washed with warm water. After drying, 22g of 3,5-bis(1,1-dimethylethyl)benzaldehyde was obtained.

47g of malonic acid and 208,8 dioxan was introduced into a flask equipped with a reflux condenser and a deep tube. Gaseous NH<sub>3</sub> was bubbled through the deep tube until ammonium malonate formed. 60g of 3,5-bis(1,1-dimethylethyl)benzaldehyde, obtained as above, was introduced and the mixture kept under reflux at 95-100°C. After the disappearance of the solid phase, 50% of the dioxane was distilled, and the solution cooled and poured into dilute HCl. After filtration, the resultant precipitate was washed with water, dissolved in a solution of NaOH 10%, and filtered. The 3,5-bis(1,1-dimethylethyl)-4-hydroxycinnamic acid was precipitated with HCl, and after filtration dried at 80°C. Recrystallization was performed from o-xylene and dioxane. 2,4-bis(1,1-dimethylethyl)-4-ethenylphenol was obtained by dissolving the 3,5-bis(1,1-dimethylethyl)-4-hydroxycinnamic acid in dimethylsulfoxide so that the concentration thereof in the dimethyl sulfoxide was 20%, and then thermally decomposing it by heating the solution for 30 minutes at 130°C for complete decarboxylation.

The amount of 1-pentene incorporated into the copolymers, can be determined by carbon 13 nuclear magnetic resonance spectroscopy, by <sup>1</sup>H NMR spectroscopy and by IR spectroscopy. However, more simply, in the Examples, the weight percentage of 1-pentene was determined from infrared spectrum at room temperature, using the 971cm<sup>-1</sup> band for propylene and the 735cm<sup>-1</sup> band for 1-pentene. The results correlate with those obtained by the integration area of

methylene, methane and methyl by <sup>1</sup>HNMR spectra of the copolymers in 1,2-dichlorobenzene.

5 The melt flow index was measured according to the standard test method for flow rates of thermoplastics by extrusion plastometer ASTM-D 1238-90B. The melt flow index (MFI) is expressed on the basis 230°C/2.16 kg.

10 The tensile properties were determined according to the standard test method for tensile properties of plastics, ASTM D 638M-91. (Specimen type MIII; crosshead speed 100mm/min).

The impact strength was determined according to the standard test method for impact resistance of plastics and electrical insulating material, ASTM 256-92.

15 The haze was determined according to the standard test method for haze and luminous transmittance of transparent plastics ASTM D 1003-92.

20 The estimates of thermooxidation and long term heat stability were effected by ageing a film of the composition in question at 110°C in an aerated oven. The estimation of thermooxidation was made by measuring by IR spectroscopy at 1720cm<sup>-1</sup> the carbonyl peak of carbonyl which formed due to the oxidation of the copolymer. The lower the increase of the carbonyl formation, the higher is the thermooxidative stability. The results are expressed as % of the carbonyl increase in 365 days. The estimation of the long term heat stability was made by visual inspection during exposure for lack of any local embrittlement. The estimation of local embrittlement was according to DIN 53383/1975, chapter 2.3.

25 Thus, in Examples 1 - 5, the continuous variation in the ratio of the concentration of propylene to that of 1-pentene was achieved as a result of the monomers being

consumed at unequal rates during the reaction; in addition, the propylene was added continuously over a period of time with the flow rate thereof into the reactor being kept constant so that the pressure increased continuously, while the 1-pentene was added only at the start of the reaction so that its concentration thus decreased as the reaction progressed. In Examples 6 - 10, the entire quantity of 1-pentene used was again added to the reactor at the start of the reaction so that its concentration decreased continuously as the reaction progressed, while the propylene was added continuously, with its flow rate being adjusted to maintain a predetermined pressure in the reactor so that the propylene partial pressure in the reactor increased continuously.

The copolymers obtained from the process according to the invention have a good balance between application properties on the physical mechanical and the optical sides. Analysis of the polymer, when related for each particular case to the application properties, show that the specificity of the comonomer and the non-uniformity or randomness of the copolymer structure are the principle factors influencing the effects obtained.

More specifically, the comonomer 1-pentene enhances certain properties of polypropylene polymers. This arises firstly from the specific length of 1-pentene. This specific length, combined with the composition, controls the crystallinity of the copolymers. Secondly, the copolymers obtained under a certain feed composition have a random distribution which is determined by the ratio of the reactivity between 1-propylene and 1-pentene. It is an important feature of this invention that the ratio of the concentration of 1-pentene to that of 1-propylene in the reaction system changes continuously, and the composition of the copolymer which is formed thus also changes continuously. This provides a unique tool for obtaining a

5 large variety of propylene/1-pentene copolymers whose properties are controlled by the non-uniformity or randomness obtained according to each particular set of reaction conditions utilized, as is evident from the Examples.

10 According to this invention, a random propylene copolymer with 1-pentene having good melt flow and mould properties as well as good transparency is produced. Properties such as flexibility and impact strength, can be controlled easily. Films of low haze, ie good transparency, are suitable for packaging and, among others, pipes, coatings, injection and flow moulding articles can be produced.

15 The resultant random thermoplastic copolymers thus have crystalline and amorphous sequences. It has also been found that the copolymers have, as stated hereinbefore, a good balance between application properties. Thus, the copolymers retained good tensile strength at yield, have high impact strength and good optical properties, ie low haze.

20 The invention thus provides a propylene/1-pentene copolymer composition which is excellent as regards thermooxidative stability and long term heat stability.

25 The use of a monomeric phenolic stabilizer grafted onto the copolymer chain prevents or inhibits the loss of the antioxidant during processing as a result of volatility, migration or extraction with solvents.

30 The use of a mixture of an organic phenolic stabilizer with a monomeric phenolic stabilizer grafted onto the copolymer is an exceptional combination which brings about the best short and long term stabilization effects.

The use of an organic phosphite together with a phenolic antioxidant and especially with a mixture of an organic phenolic antioxidant and a monomeric phenolic antioxidant grafted onto the copolymer chain increases the stability of the propylene/ 1-pentene copolymer to thermooxidative degradation and is believed to be the optimum for long term heat stability.

CLAIMS:

1. A copolymer of propylene and 1-pentene.
2. A copolymer according to Claim 1, which has a random arrangement of propylene and 1-pentene, is thermoplastic, and has crystalline and amorphous sequences.
3. A copolymer according to Claim 1 or Claim 2, wherein about 0,05% to 20% by mass of the copolymer is derived from 1-pentene, with the balance thus being derived from propylene.
4. A copolymer according to any one of Claims 1 to 3 inclusive, wherein the melt flow index of the copolymer is in the range of about 0,01 to about 200g/10 minutes.
5. A copolymer according to any one of Claims 1 to 4 inclusive, which complies with the formula
$$IS > 0,5 Y + 5$$
where IS is the impact strength of the copolymer, expressed in Kj/m<sup>2</sup>, and Y is the weight percent of 1-pentene in the copolymer.
6. A copolymer according to any one of Claims 1 to 5 inclusive, which has a haze value lower than 7,5% when measured according to ASTM 1003-92, on a film of 100µm.
7. A copolymer according to any one of Claims 1 to 6 inclusive, which is that obtained by reacting propylene and 1-pentene in a reaction zone, while maintaining a pressure between 1 and 60 kg/cm<sup>2</sup> in the zone, at a reaction temperature between 0°C and 100°C, and for a reaction time between 20 minutes and 8 hours, in the presence of a suitable Ziegler-Natta catalyst or catalyst system.

8. A copolymer according to Claim 7, which is that obtained by, in the reaction of propylene and 1-pentene in the reaction zone, continuously varying the ratio of the concentration of the propylene to that of 1-pentene in the reaction zone.

9. A process for producing a copolymer, which process comprises reacting propylene and 1-pentene in a reaction zone, while maintaining a pressure between 1 and 60 kg/cm<sup>2</sup> in the zone, at a reaction temperature between 0°C and 100°C, and for a reaction time between 20 minutes and 8 hours, in the presence of a suitable Ziegler-Natta catalyst or catalyst system.

10. A process according to Claim 9, which includes varying the ratio of the concentration of the propylene to that of the 1-pentene in the reaction zone continuously, so that the copolymer has a random arrangement of propylene and 1-pentene.

11. A process according to Claim 9 or Claim 10, wherein the reaction temperature is in the range of 20°C - 80°C, while the zone or reaction pressure is in the range 3 - 30 kg/cm<sup>2</sup>, with the reaction being continued for a sufficient period of time to obtain a monomer conversion of 10% - 95%.

12. A process according to any one of Claims 9 to 11 inclusive, wherein a single reaction zone is used and wherein the reaction is carried out in a slurry phase in which the monomers and/or the catalyst are suspended in an inert slurrying agent comprising a saturated, aliphatic or cyclo-aliphatic liquid hydrocarbon, with sufficient slurrying agent being used to achieve a slurry concentration of 4g - 400g of polymer per liter of slurrying agent.

13. A process according to any one of Claims 9 to 12 inclusive, which includes regulating the molecular weight of the copolymer by adding hydrogen to the reaction zone.

5 14. A process according to any one of Claim 9 to 13 inclusive, wherein a catalyst system comprising a titanium-based Ziegler-Natta catalyst and, as a co-catalyst, an organo-aluminium compound, and with the atomic ratio of aluminium to titanium in the catalyst system being between 0,1:1 and 100:1, is used, with  
10 sufficient of the titanium-based Ziegler-Natta catalyst being used such that the concentration of titanium is at least 0,0001 mole %, based on the total monomer addition to the reaction zone.

15 15. A polymer composition, which comprises  
as component (i), a copolymer of propylene and 1-pentene;  
as component (ii), at least one phenolic stabilizer;  
and  
as component (iii), at least one organic phosphite  
20 stabilizer; and/or  
as component (iv), at least one thioether stabilizer;  
and/or  
as component (v), at least one metal salt of a higher aliphatic acid, with the proviso that at least one of  
25 components (iii), (iv) and (v) is present.

16. A polymer composition according to Claim 15, wherein the copolymer of propylene and 1-pentene is in accordance with any one of Claims 2 to 8 inclusive.

30 17. A polymer composition according to Claim 15 or Claim 16, wherein component (ii) comprises an organic phenolic stabilizer having a molecular mass exceeding 300 and/or a monomeric phenolic stabilizer.

18. A polymer composition according to any one of Claims 15 to 17 inclusive, wherein component (iii) is present, with the organic phosphite stabilizer having a molecular mass in excess of 300.

5 19. A polymer composition according to any one of Claims 15 to 18 inclusive, wherein component (iv) is present, with the thioether stabilizer being selected from the group consisting in dilauryl thiodipropionate, distearyl thiodipropionate, dimyristyl thiodipropionate,  
10 and dioctadecyl disulphide.

20. A polymer composition according to any one of Claims 15 to 19 inclusive, wherein component (v) is present, with the metal salt being an alkaline earth metal salt, an alkali metal salt, a zinc salt, a cadmium salt, or  
15 a lead salt of stearic acid, lauric acid, capric acid or palmitic acid.

21. A polymer composition according to any one of Claims 15 to 17 inclusive, which comprises

20	component (i)	-	about 100 parts by mass
	component (ii)	-	0,01 - 1 part by mass
	component (v)	-	0,01 - 3 parts by mass

22. A polymer composition according to any one of Claims 15 to 17 inclusive, which comprises

25	component (i)	-	about 100 parts by mass
	component (ii)	-	0,01 - 1 part by mass
	component (iii)	-	0,01 - 1 part by mass
	component (v)	-	0,01 - 3 parts by mass

23. A polymer composition according to any one of Claims 15 to 17 inclusive, which comprises

- |   |                |   |                         |
|---|----------------|---|-------------------------|
|   | component (i)  | - | about 100 parts by mass |
|   | component (ii) | - | 0,01 - 1 part by mass   |
| 5 | component (iv) | - | 0,01 - 3 parts by mass  |
|   | component (v)  | - | 0,01 - 3 parts by mass  |

24. A novel copolymer, substantially as described and exemplified herein.

25. A novel process for producing a copolymer,  
10 substantially as described and exemplified herein.

26. A novel copolymer composition, substantially as described and exemplified herein.

## INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/GB 96/00201

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F210/06 C08F210/14 C08K5/00 //(C08K5/00,5:13,5:524)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 597 119 (MITSUI PETROCHEMICAL IND) 18 May 1994 see page 2, line 55 - line 57 see page 5, line 12 ---	1-8,24
X	GB,A,1 154 544 (EASTMAN KODAK) 11 June 1969 see page 3, line 108 see page 4, example 12, lines 86-93 ---	1-8,24
X	US,A,3 859 386 (MAINORD KENNETH R) 7 January 1975 see col. 4, example 1, line 64 ---	1-8,24
X	EP,A,0 541 273 (MOBIL OIL CORP) 12 May 1993 see page 3, line 40 ---	1-8,24
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"A" document member of the same patent family

Date of the actual completion of the international search

29 April 1996

Date of mailing of the international search report

07.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Mergoni, M

# INTERNATIONAL SEARCH REPORT

Inter. Application No  
PCT/GB 96/00201

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 014, no. 260 (P-1056), 5 June 1990 & JP,A,02 072311 (MITSUI PETROCHEM IND LTD), 12 March 1990, see abstract ---	15-23,26
A	EP,A,0 567 117 (PHILLIPS PETROLEUM CO) 27 October 1993 see claim 1; page 2, lines 21-25; page 7, lines 51-52 ---	15-23,26
A	EP,A,0 303 894 (AMERICAN CYANAMID CO) 22 February 1989 see claim 1 ---	15-23,26
A	EP,A,0 630 916 (MITSUI PETROCHEMICAL IND) 28 December 1994 see claim 1 -----	9-23,25, 26

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 96/00201

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0597119	18-05-94	CA-A- 2114236 WO-A- 9324567 JP-A- 6041364	09-12-93 09-12-93 15-02-94
GB-A-1154544	11-06-69	DE-A- 1720566 US-A- 3480580	01-07-71 25-11-69
US-A-3859386	07-01-75	NONE	
EP-A-0541273	12-05-93	US-A- 5153074 US-A- 5192620 US-A- 5175054 CA-A- 2081503	06-10-92 09-03-93 29-12-92 06-05-93
EP-A-0567117	27-10-93	US-A- 5310771 JP-A- 6016875	10-05-94 25-01-94
EP-A-0303894	22-02-89	JP-A- 1062360	08-03-89
EP-A-0630916	28-12-94	CA-A- 2037002 CN-A,B 1054425 CN-A,B 1064689 CN-A,B 1064690 CN-A,B 1064489 EP-A- 0450304 JP-A- 3296512 KR-B- 9403955 PL-B- 167984 US-A- 5290896 CA-A- 2037025 EP-A- 0444606 JP-A- 4249557 PL-B- 168645 PL-B- 167983 US-A- 5324805 JP-A- 4249558 JP-A- 4249559 JP-A- 4249560 CN-A,B 1055368 JP-A- 4249561	28-08-91 11-09-91 23-09-92 23-09-92 16-09-92 09-10-91 27-12-91 09-05-94 30-12-95 01-03-94 28-08-91 04-09-91 04-09-92 29-03-96 30-12-95 28-06-94 04-09-92 04-09-92 04-09-92 16-10-91 04-09-92

### Information on patent family members

PCT/GB 96/00201

Form PCT/ISA/210 (patent family annex) (July 1992)